

Neodymium: Yttrium Aluminum Garnet - Nd:YAG

SYNOPTICS manufactures Nd:YAG for use in industrial, medical, military and scientific applications. YAG is grown utilizing the Czochralski technique. The as-grown crystals are then processed into laser rods or slabs, coated in house and inspected per customer specifications. SYNOPTICS' high volume capacity and complete capabilities for growth, fabrication, polishing, and coating makes us the clear choice as your Nd:YAG rod supplier.

Advantages Of Nd:YAG Include:

- High gain
- Low threshold
- High efficiency
- Low loss at 1.06 μm
- Good thermal conductivity and thermal shock characteristics
- Mechanical strength
- High optical quality
- Material characteristics that allow for various modes of operation
- (CW, pulsed, Q-switched, mode locked, and cavity dumped)

Standard Rod Specifications

Nd Concentrations Available	0.6 – 1.3 \pm 0.1 at %
Wavefront Distortion	> λ / 4 per inch of rod length (λ = 632 nm) standard > λ / 16 per inch of rod length Opto-Lase
Extinction Ratio	25 dB minimum

Dimensional / Mechanical Specifications

Diameter Tolerance	+ .000" / - .002"
Length Tolerance	+ .040" / - .000"
Rod End Polished Flatness	λ / 10
End Face Parallelism	within 10 arc seconds
End Face Perpendicularity	within 5 arc minutes
Chamfer	0.005" \pm 0.003" x 45°
Surface Quality	10 - 5 scratch-dig per MIL-O-1 3830A
Barrel Finish	55 \pm 5 microinches (other finishes available on request)
Standard Coating (High & Partially Reflective coatings available on request)	Anti-Reflection where R < 0.25% Durability per MIL-C-48497 Damage threshold exceeds 10 J / cm ²

NORTHROP GRUMMAN

SYNOPTICS

Properties of Nd:YAG at 25°C (1.0 at % Nd)

Formula:	$Y_{2.97}Nd_{0.03}Al_5O_{12}$
Weight % Nd:	0.725
Nd Atoms / cm ³ :	1.38×10^{20}
Wavelength:	1.064 micron
Transition:	$^4F_{3/2} - ^4I_{11/2}$
Fluorescent Lifetime:	230 μsec
Thermal Conductivity:	$0.14 \text{ W cm}^{-1} \text{ K}^{-1}$
Specific Heat:	$0.59 \text{ Jg}^{-1} \text{ K}^{-1}$
Thermal Expansion:	$6.9 \times 10^{-6} \text{ }^\circ\text{C}^{-1}$
dn / dt:	$7.3 \times 10^{-6} \text{ }^\circ\text{C}^{-1}$
Young's Modulus:	$3.17 \times 10^4 \text{ Kg / mm}^{-2}$
Poisson Ratio:	0.25

YAG Physical and Chemical Properties

Formula:	$Y_3Al_5O_{12}$
Molecular Weight:	596.7
Crystal Structure:	Cubic
Moh Hardness:	8 - 8.5
Melting Point:	1950°C (3540°F)
Density:	4.55 g / cm^{-3}

Refractive Index of YAG

Wavelength	Index n (25°C)
.8	1.8245
.9	1.8222
1.0	1.8197
1.2	1.8152
1.4	1.8121

Specifications and information are subject to change without prior notice.
 © 2011 Northrop Grumman Corporation